

TEST REPORT

No. : GZML05126294-01

Date : Dec.19,2005

Page: 1 of 2

SINO-FOREIGN JOINT VENTURE

JIANGYIN PIVOT DECORATIVE MATERIALS CO., LTD.

PIVOT INDUSTRIAL PARK, NO. 1 MENGNA ROAD, 9TH HUAXI VILLAGE, HUASHI TOWN,
JIANGYIN, JIANGSU, CHINA


The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : 华西村铝塑板,标榜铝塑板
Product or Lot No. : WBP051125F
Manufacturer : SINO-FOREIGN JOINT VENTURE
JIANGYIN PIVOT DECORATIVE MATERIALS CO., LTD.
Date of Receipt : Dec.05,2005
Test Period : Dec.05,2005 to Dec.16,2005

Test result(s) : For further details, please refer to the following page(s)


***** To be continued*****

Signed for and on behalf of
SGS-CSTC Standards
Technical Service Co., Ltd.



Michael Zhang
Section Head

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days only. This Test Report shall not be reproduced except in full, without written approval of the Company.



TEST REPORT

No. : GZML05126294-01
 Date : Dec.19,2005
 Page: 2 of 2

Test Result(s):

Sample description: white aluminium-plastic composite panel

No.	Test item	Ref. standard	Test condition	Result
1	Unit weight (kg/m ²)	Supplied by client	Calculate by the weight and size	5.55
2	Heat deflection temperature (°C)	ASTM D648-01 and client's requirement	Span: 100mm; Load: 1.82MPa Heating rate: 120°C/h	98.0
3	Bending strength (MPa)	ASTM D790-03	Speed: 1.3mm/min; Span: 64mm;	112.8
4	Bending elastic modulus (MPa)			16640
5	Through resistance (kN)	ASTM D732-02	Speed: 1.3mm/min	8.4
6	180° peel strength (N/mm)	ASTM D903-98	Speed: 152.4mm/min	10.6
7	Tensile strength (MPa)	ASTM E8-04	Speed: 2.0 mm/min	41.7
8	Dry adhesion	AAMA2605-02	Cut space: 1mm Tape: 3M® 610#	More than 4B

*****End of report*****

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days only. This Test Report shall not be reproduced except in full, without written approval of the Company.

